

## ABSTRAK

Perkembangan industri yang sangat meningkat mengakibatkan dampak negatif bagi lingkungan salah satunya masalah limbah zat warna. *Malachite green* (MG) salah satu zat warna dasar yang pada umumnya digunakan pada industri tekstil. Limbah MG berbahaya jika masuk ke dalam perairan karena efek toksiknya yang tinggi. Teknik pemisahan telah dikembangkan untuk mengurangi limbah berbahaya ini, salah satunya menggunakan metode adsorpsi. Tujuan penelitian ini adalah untuk mengetahui karakteristik  $\text{SiO}_2$  dan  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  yang disintesis, studi adsorbsi, kinetika adsorpsi, isoterms adsorpsi, serta pengujian pemakaian berulang  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  dan  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$ .  $\text{SiO}_2$  diekstrak dari limbah abu layang menggunakan metode sol gel. Senyawa  $\text{SiO}_2$  yang dihasilkan berupa padatan kasar berwarna putih, kemudian digunakan untuk melapisi magnetit ( $\text{Fe}_3\text{O}_4$ ) termodifikasi kitosan. Hasil sintesis  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  berupa padatan berwarna hitam dan dapat ditarik menggunakan magnet. Senyawa  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  kemudian dikarakterisasi menggunakan instrumen FTIR dan XRD. Analisis FTIR menunjukkan adanya serapan  $-\text{NH}$  pada daerah  $1620 \text{ cm}^{-1}$ , serapan  $\text{Fe}-\text{O}$  pada daerah  $586 \text{ cm}^{-1}$ , dan serapan  $\text{Si}-\text{O}-\text{Si}$  pada daerah  $435 \text{ cm}^{-1}$ . Hasil XRD menunjukkan terbentuknya  $\text{Fe}_3\text{O}_4$  dengan struktur kubik. Kondisi optimum adsorpsi MG oleh  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  dan  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  pada pH 6, waktu kontak masing-masing selama 80 dan 60 menit. Adsorpsi MG mengikuti kinetika pseudo orde dua dan Isoterm Langmuir dengan nilai  $q_{\text{maks}}$   $\text{Fe}_3\text{O}_4@\text{SiO}_2$  dan  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  berturut-turut sebesar 32,0512 dan 51,2820 mg/g. Selain itu, dilakukan pengujian pemakaian berulang sebanyak tiga kali untuk  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  dan  $\text{Fe}_3\text{O}_4@\text{SiO}_2-\text{CS}$  memberikan hasil desorpsi sebesar 32-50% dan 51-65%.

**Kata Kunci:** kitosan,  $\text{Fe}_3\text{O}_4$ ,  $\text{SiO}_2$ , *malachite green*, abu layang

## **ABSTRACT**

*The rapid development of the industry has led to negative environmental impacts, one of which is the problem of industrial waste containing dyes. Malachite green (MG) is widely used, especially in the textile industry. MG dye waste is dangerous if it enters water due to high toxicity. Separation techniques have been developed to reduce this dangerous waste, including the use of adsorption methods. The objective of this research is to determine the characteristics of synthesized  $\text{SiO}_2$  and  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$ , adsorption studies, adsorption kinetics, adsorption isotherms, and the reusability of  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  and  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$ .  $\text{SiO}_2$  is extracted from fly ash waste using the sol-gel method. The resulting  $\text{SiO}_2$  compound is a coarse white solid, which is then used to coat chitosan-modified magnetite ( $\text{Fe}_3\text{O}_4$ ). The synthesized  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$  compound is a black solid that can be attracted using a magnet. The  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$  compound is characterized using FTIR and XRD instruments. FTIR analysis shows absorption peaks at  $1620 \text{ cm}^{-1}$  for -NH,  $586 \text{ cm}^{-1}$  for Fe-O, and  $435 \text{ cm}^{-1}$  for Si-O-Si. XRD results indicate the formation of cubic  $\text{Fe}_3\text{O}_4$ . The optimum adsorption conditions for MG by  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  and  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$  are at pH 6, with contact times 80 and 60 minutes. MG adsorption follows pseudo-second-order kinetics and Langmuir isotherms, with maximum adsorption capacities ( $q_{\text{maks}}$ ) 32,0512 and 51,2820 mg/g for  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  and  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$ . Furthermore, reusability test for  $\text{Fe}_3\text{O}_4@\text{SiO}_2$  and  $\text{Fe}_3\text{O}_4@\text{SiO}_2\text{-CS}$  was conducted three times, resulting in desorption yields 32-50% and 51-65%.*

**Keywords:** chitosan,  $\text{Fe}_3\text{O}_4$ ,  $\text{SiO}_2$ , malachite green, fly ash